

# PHYSICAL TESTING REPORT

# LUCIDEON

insight creating advantage



0013

## Granula

Office 202a  
Building 7  
12 Sibirsk Tract  
Yekaterinburg City  
620100  
Russian Federation

FAO: Mr. Alex Tsypkin

**Report of Tests on:** 2. Granulite 300

**Your Reference:** Cenosphere Granulite 300

**Lucideon Reference:** (172820)-20832

**Date Reported:** 21-Jul-2017

**Order Number:** None

**Date Logged:** 26-Jun-2017

**Date(s) of Test(s):** 14-Jul-2017 to 20-Jul-2017

### Determination of Refractoriness (PCE)

ASTM C24-09(13) Using Orton Pyrometric Reference Cones

### Test Results:

Cone: 31.5 - 32

Temperature: 1699-1717 °C

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

**End of Test Report**

Miss Zoe Kinally  
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited  
Queens Road, Penkull  
Stoke-on-Trent  
Staffordshire ST4 7LQ

T +44 (0)1782 764428  
enquiries@lucideon.com  
www.lucideon.com

Page 1 of 1

# INORGANIC ANALYSIS REPORT



0013

**Granula**  
Office 202a  
Building 7  
12 Sibirsk Tract  
Yekaterinburg City  
620100  
Russian Federation

FAO: Mr. Alex Tsyarkin

**Report of Tests on:** 2. Granulite 300

**Your Reference:** Cenosphere Granulite 300

**Lucideon Reference:** (172820)-20832

**Date Reported:** 29-Jun-2017

**Order Number:** None

**Date Logged:** 26-Jun-2017

**Date(s) of Test(s):** 28-Jun-2017 to 29-Jun-2017

## XRF Analysis

Methods C201 based on BSEN ISO 12677:2011

Result(s)		Units	
Sample Basis			Dried 110 deg C
Silicon Dioxide	SiO <sub>2</sub>	%	59.10
Titanium Dioxide	TiO <sub>2</sub>	%	1.05
Aluminium Oxide	Al <sub>2</sub> O <sub>3</sub>	%	34.44
Iron (III) Oxide	Fe <sub>2</sub> O <sub>3</sub>	%	1.43
Calcium Oxide	CaO	%	0.76
Magnesium Oxide	MgO	%	0.28
Potassium Oxide	K <sub>2</sub> O	%	0.59
Sodium Oxide	Na <sub>2</sub> O	%	0.41
Phosphorus Pentoxide	P <sub>2</sub> O <sub>5</sub>	%	0.35
Chromium (III) Oxide	Cr <sub>2</sub> O <sub>3</sub>	%	<0.01
Manganese (II,III) Oxide	Mn <sub>3</sub> O <sub>4</sub>	%	0.03
Zirconium Oxide	ZrO <sub>2</sub>	%	0.03
Hafnium (IV) Oxide	HfO <sub>2</sub>	%	<0.01
Lead Oxide	PbO	%	<0.02
Zinc Oxide	ZnO	%	<0.01
Barium Oxide	BaO	%	0.14
Strontium (II) Oxide	SrO	%	0.05
Tin (IV) Oxide	SnO <sub>2</sub>	%	<0.01
Copper Oxide	CuO	%	0.01
Loss on Ignition		%	0.96
Loss on Ignition Temperature		°C	1000
Total		%	99.63
Sulphur Trioxide	SO <sub>3</sub>	%	<0.05
UKAS Accredited			Yes

The sulphur trioxide may not be a total sulphur figure but is the sulphur remaining after LOI and fusion. Results are quoted to 2 decimal places but are accurate to 3 significant figures or the number of figures given, whichever is the lesser.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

**End of Test Report**

Mr Josh Rushton  
Technician

**PHYSICAL TESTING ANALYSIS REPORT**

**Description:** Determination of Particle Size Distribution

**Test Method:** In House Method PT55

**Lucideon Reference:** (172820)-20831

**Client:** Granula  
Office 202a  
Building 7  
12 Sibirsk Tract  
Yekaterinburg City  
620100  
Russian Federation

**For the Attention of:** Mr. Alex Tsyarkin

**Date Logged:** 26-Jun-2017

**Date of Tests:** 03-Jul-2017 to 03-Jul-2017

**Report Date:** 03-Jul-2017

**Purchase Order No.:** None

Please find attached the results for the sample(s) recently submitted for analysis.



**Mr Simon Hall  
Manager**

# Lucideon Analysis Report

Created by: burton  
Last edited: 12/06/2017 10:56:09



## Measurement Details

**Sample Name** (172820)-20832 Granula - 2 Granulite 300 - Cenosphere Granulite 300  
**Measurement Date Time** 03/07/2017 11:24:50  
**Operator Name** Burton  
**Analysis Date Time** 03/07/2017 11:24:50  
**SOP File Name** HydroEV.cfg  
**Result Source** Measurement


## Analysis

**Particle Name** Aluminium silicate  
**Particle Refractive Index** 1.650  
**Dispersant Name** Propan-2-ol  
**Dispersant Refractive Index** 1.390  
**Particle Absorption Index** 0.100  
**Laser Obscuration** 14.27 %  
**Weighted Residual** 0.22 %  
**Scattering Model** Mie  
**Analysis Model** General Purpose  
**Analysis Sensitivity** Normal

## Result

**Concentration** 0.1955 %  
**Uniformity** 0.428  
**Specific Surface Area** 60.65 m<sup>2</sup>/kg  
**D [3,2]** 98.9 µm  
**D [4,3]** 128 µm  
**Span** 1.397  
**Result Units** Volume  
**Dv (10)** 56.5 µm  
**Dv (50)** 116 µm  
**Dv (90)** 219 µm

## Frequency (compatible) and Undersize



Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under
0.0100	0.00	0.0876	0.00	0.767	0.00	6.72	0.00	58.9	11.28	516	100.00
0.0114	0.00	0.0995	0.00	0.872	0.00	7.64	0.00	66.9	16.31	586	100.00
0.0129	0.00	0.113	0.00	0.991	0.00	8.68	0.00	76.0	22.51	666	100.00
0.0147	0.00	0.128	0.00	1.13	0.00	9.86	0.00	86.4	29.81	756	100.00
0.0167	0.00	0.146	0.00	1.28	0.00	11.2	0.00	98.1	38.04	859	100.00
0.0189	0.00	0.166	0.00	1.45	0.00	12.7	0.00	111	46.96	976	100.00
0.0215	0.00	0.188	0.00	1.65	0.00	14.5	0.00	127	56.23	1110	100.00
0.0244	0.00	0.214	0.00	1.88	0.00	16.4	0.00	144	65.44	1260	100.00
0.0278	0.00	0.243	0.00	2.13	0.00	18.7	0.00	163	74.16	1430	100.00
0.0315	0.00	0.276	0.00	2.42	0.00	21.2	0.00	186	81.98	1630	100.00
0.0358	0.00	0.314	0.00	2.75	0.00	24.1	0.07	211	88.55	1850	100.00
0.0407	0.00	0.357	0.00	3.12	0.00	27.4	0.23	240	93.62	2100	100.00
0.0463	0.00	0.405	0.00	3.55	0.00	31.1	0.60	272	97.16	2390	100.00
0.0526	0.00	0.460	0.00	4.03	0.00	35.3	1.32	310	99.28	2710	100.00
0.0597	0.00	0.523	0.00	4.58	0.00	40.1	2.57	352	100.00	3080	100.00
0.0679	0.00	0.594	0.00	5.21	0.00	45.6	4.53	400	100.00	3500	100.00
0.0771	0.00	0.675	0.00	5.92	0.00	51.8	7.38	454	100.00		



Size (µm)	% Volume In	Size (µm)	% Volume In	Size (µm)	% Volume In	Size (µm)	% Volume In	Size (µm)	% Volume In	Size (µm)	% Volume In		
0.0100	0.00	0.0679	0.00	0.460	0.00	3.12	0.00	21.2	0.07	144	8.73	976	0.00
0.0114	0.00	0.0771	0.00	0.523	0.00	3.55	0.00	24.1	0.16	163	7.82	1110	0.00
0.0129	0.00	0.0876	0.00	0.594	0.00	4.03	0.00	27.4	0.37	186	6.56	1260	0.00
0.0147	0.00	0.0995	0.00	0.675	0.00	4.58	0.00	31.1	0.72	211	5.08	1430	0.00
0.0167	0.00	0.113	0.00	0.767	0.00	5.21	0.00	35.3	1.25	240	3.54	1630	0.00
0.0189	0.00	0.128	0.00	0.872	0.00	5.92	0.00	40.1	1.96	272	2.12	1850	0.00
0.0215	0.00	0.146	0.00	0.991	0.00	6.72	0.00	45.6	2.85	310	0.71	2100	0.00
0.0244	0.00	0.166	0.00	1.13	0.00	7.64	0.00	51.8	3.90	352	0.00	2390	0.00
0.0278	0.00	0.188	0.00	1.28	0.00	8.68	0.00	58.9	5.04	400	0.00	2710	0.00
0.0315	0.00	0.214	0.00	1.45	0.00	9.86	0.00	66.9	6.20	454	0.00	3080	0.00
0.0358	0.00	0.243	0.00	1.65	0.00	11.2	0.00	76.0	7.30	516	0.00	3500	
0.0407	0.00	0.276	0.00	1.88	0.00	12.7	0.00	86.4	8.23	586	0.00		
0.0463	0.00	0.314	0.00	2.13	0.00	14.5	0.00	98.1	8.92	666	0.00		
0.0526	0.00	0.357	0.00	2.42	0.00	16.4	0.00	111	9.27	756	0.00		
0.0597	0.00	0.405	0.00	2.75	0.00	18.7	0.00	127	9.21	859	0.00		

# INORGANIC ANALYSIS REPORT



0013

**Granula**  
Office 202a  
Building 7  
12 Sibirsk Tract  
Yekaterinburg City  
620100  
Russian Federation

FAO: Mr. Alex Tsyarkin

**Report of Tests on:** 2. Granulite 300

**Your Reference:** Cenosphere Granulite 300

**Lucideon Reference:** (172820)-20832

**Date Reported:** 29-Jun-2017

**Order Number:** None

**Date Logged:** 26-Jun-2017

**Date(s) of Test(s):** 27-Jun-2017 to 28-Jun-2017

### Loss on Drying

Methods C201 based on BSEN ISO 12677:2011

Result(s)		Units	
Sample Basis			As Received
Loss on Drying Temperature		°C	110
Loss on Drying		%	0.00
UKAS Accredited			Yes

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

**End of Test Report**

Mr Josh Rushton  
Technician

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited  
Queens Road, Penkhull  
Stoke-on-Trent  
Staffordshire ST4 7LQ

T +44 (0)1782 764428  
enquiries@lucideon.com  
www.lucideon.com